



## SteelSkin™ performance level ratings.

### STANDARD EN 388:2003 -Protection from mechanical risks

Rating	0	1	2	3	4	5
A. Abrasion Resistance (cycles)	< 100	100	500	2000	8000	-
B. Blade Cut Resistance (factor)	< 1.3	1.2	2.5	5.0	10.0	20.0

### SteelSkin™ Test Results

% of SteelSkin™ Used	Abrasion	Blade Cut
6% SteelSkin™	490	2.4
6% SteelSkin™ Bonded	7000	8.6